

DP024202NC001-TDS

COCOON PLA- Cactus(HT)

It is a bio-based environmentally friendly material with high temperature resistance, extremely low warpage and shrinkage, and non-toxicity. It has no odor or dust is produced during the printing process. It is also characterized by ease of printing and molding, good heat resistance, dimensional stability, and a matte texture. It is suitable for industrial components, jigs and fixtures, and channel letters materials that require higher printing accuracy.

Part 1 Injection-Molded Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Physical Properties				
Density	23°C	GB/T 1033	g/cm ³	1.24
Melt Flow Rate	190°C, 2.16kg	GB/T 3682	g/10min	6
Mechanical Properties				
Tensile Strength	5mm/min	GB/T 1040.2	MPa	56
Elongation @ Break	5mm/min	GB/T 1040.2	%	10
Flexural Strength	2mm/min	GB/T 9341	MPa	80
Flexural Modulus	2mm/min	GB/T 9341	MPa	2700
Izod Impact Strength	2.75J	GB/T 1843	kJ/m ²	5

Note: The typical physical properties are not intended for use as sales specifications.

Part 2 Printed Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Mechanical Properties				
Tensile Strength(X-Y)	50mm/min	GB/T 1040.2	MPa	42
Tensile Strength(Z)	50mm/min	GB/T 1040.2	MPa	25
Impact Strength, Notched	2.75J	GB/T 1843	kJ/m ²	5
Flexural Strength	2mm/min	GB/T 9341	MPa	81

Note: All specimens are printed under the following conditions: nozzle temperature = 210°C, printing speed = 60 mm/s, the build plate is not heated, infill = 100%, nozzle diameter = 0.4mm.



Printing Path Direction of Specimen (Z)



Printing Path Direction of Specimen (X-Y)

Part 3 Printing Guidelines

Parameters	Settings
Nozzle Temperature	200-230°C
Build Plate Temp.	65°C
Build Plate Material	Glass、PEI、 Steel Spring Build Plate
Bottom Layer Printing Temp.	220-230°C
Enclosed-chamber Printing	/
Print Speed	60-200mm/s
Drying recommendations	40-50 °C in a hot air dryer for 4-8hours

Disclaimer:

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.