

# DP021001NC002-TDS

## COCOON PLA-Vine

It is a bio-based and environmentally friendly material with exceptional toughness and safety. It features low shrinkage, minimal warping, stable extrusion, and easy printability, presenting a semi-transparent, slightly translucent texture. It is suitable for 3D printing applications that require toughness and precision, such as aesthetic detail models or complex industrial design prototypes.

### Part 1 Injection-Molded Specimen Performance


Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Physical Properties				
Density	23°C	GB/T 1033	g/cm <sup>3</sup>	1.24
Melt Volume Rate	190°C, 2.16kg	GB/T 3682	g/10min	5
Mechanical Properties				
Tensile Strength	5mm/min	GB/T 1040.2	MPa	60
Elongation @ Break	5mm/min	GB/T 1040.2	%	5
Flexural Strength	2mm/min	GB/T 9341	MPa	90
Flexural Modulus	2mm/min	GB/T 9341	MPa	2800
Izod Impact Strength	2.75J	GB/T 1843	kJ/m <sup>2</sup>	8

*Note: The typical physical properties are not intended for use as sales specifications.*

### Part 2 Printed Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Mechanical Properties				
Tensile Strength(X-Y)	50mm/min	GB/T 1040.2	MPa	61
Tensile Strength(Z)	50mm/min	GB/T 1040.2	MPa	30
Flexural Strength	2mm/min	GB/T 9341	MPa	85
Flexural Modulus	2mm/min	GB/T 9341	MPa	2800
Impact Strength, Notched	2.75J	GB/T 1843	kJ/m <sup>2</sup>	5

*Note: All specimens are printed under the following conditions: nozzle temperature = 200°C, printing speed = 130 mm/s, build plate temperature=60°C infill = 100%, nozzle diameter = 0.4mm.*



Printing Path Direction of Specimen (Z)



Printing Path Direction of Specimen (X-Y)

### Part 3 Printing Guidelines

Parameters	Settings
Nozzle Temperature	190-220°C
Build Plate Temp.	50-65°C
Build Plate Material	Glass、 PEI、 Steel Spring Build Plate
Bottom Layer Printing Temp.	200-210°C
Enclosed-chamber Printing	/
Print Speed	60-200mm/s
Drying recommendations	40-50 °C in a hot air dryer for 4-8hours

=

#### Disclaimer:

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.