

# EP092306NC001-TDS

## COCOON PET-Cactus(HTGF)

COCOON PET-Cactus(HTGF) is a glass fiber reinforced, heat-resistant consumable, offering an "enhanced, heat-resistant" solution for 3D printed PET materials. It boasts a heat deflection temperature of up to 182°C without the need for annealing or waiting. This consumable also features high heat resistance, high strength, high stiffness, and high creep resistance, along with good fluidity and stable extrusion performance. The printed products have a matte and frosted texture, with high heat resistance and mechanical strength. They are waterproof, have excellent chemical resistance, and combine outstanding mechanical properties with good dimensional stability, making them widely applicable in functional components, load-bearing structures, and auxiliary tooling fixtures for 3D printing scenarios involving long-term loads.

### Part 1 Injection-Molded Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Physical Properties				
Density	23°C	GB/T 1033	g/cm <sup>3</sup>	1.41
Melt Volume Rate	275°C,2.16kg	GB/T 3682	g/10min	35
Mechanical Properties				
Tensile Strength	5mm/min	GB/T 1040.2	MPa	100
Elongation @ Break	5mm/min	GB/T 1040.2	%	5
Flexural Strength	2mm/min	GB/T 9341	MPa	160
Flexural Modulus	2mm/min	GB/T 9341	MPa	5200
Izod Impact Strength	1J	GB/T 1843	kJ/m <sup>2</sup>	6

*Note: The typical physical properties are not intended for use as sales specifications.*

## Part 2 Printed Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Mechanical Properties				
Tensile Strength(X-Y)	50mm/min	GB/T 1040.2	MPa	110
Tensile Strength(Z)	50mm/min	GB/T 1040.2	MPa	36
Flexural Strength	2mm/min	GB/T 9341	MPa	156
Flexural Modulus	2mm/min	GB/T 9341	MPa	4800
Impact Strength, Notched	2.75J	GB/T 1843	kJ/m2	16
Thermal Property				
HDT	1.8MPa	GB/T 1634	°C	182

*Note: All specimens are printed under the following conditions: nozzle temperature = 300°C, printing speed = 80 mm/s, build plate temperature=90°C infill = 100%, nozzle diameter = 0.4mm.*



Printing Path Direction of Specimen (Z)



Printing Path Direction of Specimen (X-Y)

## Part 3 Printing Guidelines

Parameters	Settings
Nozzle Temperature	280-320°C
Build Plate Temp.	80-100°C
Build Plate Material	Glass、PEI、 Steel Spring Build Plate
Bottom Layer Printing Temp.	/
Enclosed-chamber Printing	yes
Print Speed	60-100mm/s
Drying recommendations	80 °C in a hot air dryer for 4hours

Disclaimer:

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.