

EP061010NC002-TDS

COCOON ABS-Vine(HS)

It is an ABS material supporting high-speed and open printing. With high fluidity and low heat capacity, it can realize the rapid melting and cooling of the material, effectively maintaining the details of the effect of high-speed printing. Printing speed in high-speed printers can reach a maximum of 200mm/s. The heat-resistant temperature of the printed parts can reach 80~82°C, taking into account the printing efficiency, printing performance, heat-resistant performance and convenience of operation. At the same time, it has excellent mechanical properties and reliable dimensional stability. It is widely used in toys and blocks, electronic and electrical shell parts, industrial parts and fixtures.

Part 1 Injection-Molded Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Physical Properties				
Density	23°C	GB/T 1033	g/cm ³	1.11
Melt Volume Rate	220°C, 10kg	GB/T 3682	g/10min	150
Mechanical Properties				
Tensile Strength	5mm/min	GB/T 1040.2	MPa	40
Elongation @ Break	5mm/min	GB/T 1040.2	%	10
Flexural Strength	2mm/min	GB/T 9341	MPa	60
Flexural Modulus	2mm/min	GB/T 9341	MPa	2400
Izod Impact Strength	1J	GB/T 1843	kJ/m ²	4

Note: The typical physical properties are not intended for use as sales specifications.

Part 2 Printed Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Mechanical Properties				
Tensile Strength(X-Y)	50mm/min	GB/T 1040.2	MPa	45
Tensile Strength(Z)	50mm/min	GB/T 1040.2	MPa	26
Flexural Strength	2mm/min	GB/T 9341	MPa	63
Flexural Modulus	2mm/min	GB/T 9341	MPa	2200
Impact Strength, Notched	2.75J	GB/T 1843	kJ/m ²	4

Note: All specimens are printed under the following conditions: nozzle temperature = 270°C, printing speed = 150 mm/s, build plate temperature=85°C infill = 100%, nozzle diameter = 0.4mm.



Printing Path Direction of Specimen (Z)



Printing Path Direction of Specimen (X-Y)

Part 3 Printing Guidelines

Parameters	Settings
Nozzle Temperature	260-290°C
Build Plate Temp.	80-90°C
Build Plate Material	Glass、PEI、 Steel Spring Build Plate
Bottom Layer Printing Temp.	/
Enclosed-chamber Printing	Support open printing / Enclosed printing provides better results
Print Speed	100-200mm/s
Drying recommendations	60 °C in a hot air dryer for 4hours

Disclaimer:

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.