

EP081001TR001-TDS

COCOON PETG-Basic

It is a translucent 3D printing material characterized by high fluidity, excellent chemical resistance, balanced performance, and ease of printability. Parts printed with this material exhibit good toughness, low warpage, high surface gloss, and refined translucency. They are resistant to chemical corrosion, weathering, and yellowing, while also being eco-friendly and free of Bisphenol A. This material is suitable for 3D printing applications requiring enhanced toughness and impact resistance, aesthetic models with specific surface quality demands, household appliance accessories, electronic product components, cosmetic containers, and more.

Part 1 Injection-Molded Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Physical Properties				
Density	23°C	GB/T 1033	g/cm ³	1.28
Mechanical Properties				
Tensile Strength	5mm/min	GB/T 1040.2	MPa	50
Elongation @ Break	5mm/min	GB/T 1040.2	%	5
Flexural Strength	2mm/min	GB/T 9341	MPa	70
Flexural Modulus	2mm/min	GB/T 9341	MPa	2200
Izod Impact Strength	2.75J	GB/T 1843	kJ/m ²	5
Thermal Property				
HDT	0.45MPa	GB/T 1634	°C	75

Note: The typical physical properties are not intended for use as sales specifications.

Part 2 Printed Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Mechanical Properties				
Tensile Strength(X-Y)	50mm/min	GB/T 1040.2	MPa	58
Tensile Strength(Z)	50mm/min	GB/T 1040.2	MPa	31
Flexural Strength	2mm/min	GB/T 9341	MPa	81
Flexural Modulus	2mm/min	GB/T 9341	MPa	2200
Impact Strength, Notched	2.75J	GB/T 1843	kJ/m ²	4

Note: All specimens are printed under the following conditions: nozzle temperature = 250°C, printing speed = 100 mm/s, build plate temperature=75°C infill = 100%, nozzle diameter = 0.4mm.



Printing Path Direction of Specimen (Z)



Printing Path Direction of Specimen (X-Y)

Part 3 Printing Guidelines

Parameters	Settings
Nozzle Temperature	250°C
Build Plate Temp.	75°C
Build Plate Material	Glass、PEI、 Steel Spring Build Plate
Bottom Layer Printing Temp.	250°C
Enclosed-chamber Printing	/
Print Speed	60-150mm/s
Drying recommendations	60°C, 4-8h

Disclaimer:

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.