

# EP072206NC002-TDS

## COCOON ASA-Vine

COCOON ASA-Vine is an easy-to-print series of filaments that features high strength, high rigidity, weather resistance, anti-yellowing, anti-aging, and corrosion resistance. It is easy to print, with low risk of cracking and warping, and supports an open printing environment. The printed items are strong and sturdy, with a matte frosted surface texture, making it suitable for end-use parts that require certain strength or weather resistance, such as automotive interior parts, garden furniture, and outdoor recreational facilities.

### Part 1 Injection-Molded Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Physical Properties				
Density	23°C	GB/T 1033	g/cm <sup>3</sup>	1.17
Melt Volume Rate	220°C,10kg	GB/T 3682	g/10min	10
Mechanical Properties				
Tensile Strength	5mm/min	GB/T 1040.2	MPa	60
Elongation @ Break	5mm/min	GB/T 1040.2	%	5
Flexural Strength	2mm/min	GB/T 9341	MPa	85
Flexural Modulus	2mm/min	GB/T 9341	MPa	3500
Izod Impact Strength	1J	GB/T 1843	kJ/m <sup>2</sup>	6

*Note: The typical physical properties are not intended for use as sales specifications.*

## Part 2 Printed Specimen Performance

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Mechanical Properties				
Tensile Strength(X-Y)	50mm/min	GB/T 1040.2	MPa	45
Tensile Modulus(X-Y)	50mm/min	GB/T 1040.2	MPa	3300
Tensile Strength(Z)	50mm/min	GB/T 1040.2	MPa	22
Tensile Modulus(Z)	50mm/min	GB/T 1040.2	MPa	2000
Flexural Strength	2mm/min	GB/T 9341	MPa	63
Flexural Modulus	2mm/min	GB/T 9341	MPa	3300
Impact Strength, Notched	2.75J	GB/T 1843	kJ/m2	5

*Note: All specimens are printed under the following conditions: nozzle temperature = 260°C, printing speed = 150 mm/s, build plate temperature=95°C infill = 100%, nozzle diameter = 0.4mm.*



Printing Path Direction of Specimen (Z)



Printing Path Direction of Specimen (X-Y)

## Part 3 Printing Guidelines

Parameters	Settings
Nozzle Temperature	260°C
Build Plate Temp.	90-100°C
Build Plate Material	Glass、PEI、 Steel Spring Build Plate
Bottom Layer Printing Temp.	260°C
Enclosed-chamber Printing	Support open printing / Enclosed printing provides better results
Print Speed	100-200mm/s
Drying recommendations	80 °C in a hot air dryer for 4hours

**Disclaimer:**

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.

