

PP5701NC901-TDS

PP for 3D printing

It is a fiberglass-reinforced PP pellet material that is professionally tailored for large-scale equipment for 3D printing pellets. The material possesses characteristics such as high strength, high toughness, and easy printing, with low shrinkage and warping rates during printing. The printed products have excellent tensile and impact resistance, and are lightweight, waterproof, tough and durable, and have great chemical resistance. This material is suitable for printing functional prototypes and mechanical parts used in industrial casting, automotive manufacturing, and medical equipment fields.

Part 1 Physical Properties

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Density	23°C	ISO 1183	g/cm ³	1.12
Melt Flow Rate	230°C, 2.16kg	ISO 1133	g/10min	3

Note: The typical physical properties are not intended for use as sales specifications.

Part 2 Mechanical Properties

Testing Items	Testing Conditions	Testing Methods	Units	Typical Values
Tensile Strength	5mm/min	ISO 527-1	MPa	60
Elongation @ Break	5mm/min	ISO 527-1	%	10
Flexural Strength	2mm/min	ISO 178	MPa	65
Flexural Modulus	2mm/min	ISO 178	MPa	3500
Impact Strength, Notched	1J	ISO 179-1	kJ/m ²	40

Note: The typical physical properties are not intended for use as sales specifications.

Part 3 Recommended Processing Conditions

Parameters	Settings
Drying recommendations	80°C in a hot air dryer for 2-4hours
Extrusion Temperature	190-210°C

Disclaimer:

The values provided in this data sheet are for reference and comparison purposes only. They should not be used for design specifications or quality control. Actual values may vary depending on printing conditions. The ultimate performance of printed parts depends not only on the material but also on the part design, environmental conditions, and printing conditions. The product specifications are subject to change without notice.

Each user is responsible for determining the safety, legality, technical suitability, and disposal/recycling of the intended use. Unless otherwise stated, POLYFUL makes no warranties of any kind, express or implied, regarding the suitability of its materials for any use or application. POLYFUL shall not be liable for any damages, injuries, or losses caused by the use of POLYFUL materials in any application.